
Training a Foundation Model for Materials on a Budget

Teddy Koker Tess Smidt

Department of Electrical Engineering and Computer Science
Massachusetts Institute of Technology
Cambridge, MA 02139
{tekoker, tsmidt}@mit.edu

Abstract

Foundation models for materials modeling are advancing quickly, but their training remains expensive, often placing state-of-the-art methods out of reach for many research groups. We introduce Nequix, a compact E(3)-equivariant potential that pairs a simplified NequIP design with modern training practices, including equivariant root-mean-square layer normalization and the Muon optimizer, to retain accuracy while substantially reducing compute requirements. Built in JAX, Nequix has 700K parameters and was trained in 500 A100-GPU hours. On the Matbench-Discovery and MDR Phonon benchmarks, Nequix ranks third overall while requiring less than one quarter of the training cost of most other methods, and it delivers an order-of-magnitude faster inference speed than the current top-ranked model. We release model weights and a JAX codebase at <https://github.com/atomicarchitects/nequix>.

1 Introduction

Machine learned inter-atomic potentials (MLIPs) are rapidly improving in capability and scope, with foundation models trained on broad datasets of atomistic materials offering the promise of augmenting or replacing expensive *ab initio* density functional theory (DFT) calculations [Batatia et al., 2023]. While performance on community benchmarks such as Matbench-Discovery [Riebesell et al., 2025] is rising, the computational costs of both data generation and curation as well as the training of MLIP models on these datasets remain prohibitively expensive for many labs.

We pursue an orthogonal goal to scaling: a lower computational cost recipe that preserves strong downstream accuracy. Concretely, we revisit a simplified E(3)-equivariant architecture based on NequIP [Batzner et al., 2022] with modern training practices: root-mean-square layer normalization for stability, dynamic batching to maximize GPU utilization, and optimizer choices inspired by “speedrunning” deep learning workflows [Jordan et al., 2024a]. The resulting model, Nequix, is 700K parameters and can be trained in 500 gpu hours, while remaining competitive with larger and more costly to train models on Matbench-Discovery and other phonon prediction tasks.

Our contributions are threefold: 1) a simplified NequIP architecture featuring an equivariant layer-norm, with an efficient JAX implementation. ; 2) a budget-conscious training pipeline leveraging dynamic batching and the Muon optimizer [Jordan et al., 2024b] which achieves fast convergence; and 3) evaluations on the Matbench-Discovery and MDR phonon [Loew et al., 2025] benchmarks. Compared to prior MPtrj-trained models [Chen and Ong, 2022, Deng et al., 2023, Batatia et al., 2023, Bochkarev et al., 2024, Neumann et al., 2024, Barroso-Luque et al., 2024, Fu et al., 2025, Zhang et al., 2025, Yan et al., 2025], we rank in *third* on both benchmarks with one fourth the training cost of any other published training cost and a 10× faster inference speed over current top ranking model.




Figure 2: Validation metrics during training a smaller version of Nequix configuration with Adam and Muon, trying learning rates in $\{0.03, 0.01, 0.003, 0.001\}$ and with/without RMSNorm. This model configuration uses the same hyperparameters as the final model, except with hidden irreps of $128 \times 0e + 64 \times 1o$. The dotted horizontal line shows the best validation performance reached during the Adam training.

3 Experiments

3.1 Matbench-Discovery benchmark

Matbench-Discovery [Riebesell et al., 2025] provides a standard framework for evaluating interatomic potentials in a high-throughput materials screening task consisting of geometry optimization and energy prediction on a set of 257,487 generated structures, and thermal conductivity prediction on a set of 103 structures. Ground truth is calculated with DFT/PBE level of theory, the same as MPtrj. The primary metrics include: 1) the F1 for stable/unstable classification after relaxation; 2) root mean squared displacement (RMSD) between predicted and reference structures after relaxation; and 3) symmetric relative mean error in predicted phonon mode contributions to thermal conductivity κ (κ_{SRME}). A normalized and weighted combination of these metrics are then used to compute a combined performance score (CPS), which is used for ranking.

Following Riebesell et al. [2025] we integrate our interatomic potential as Atomic Simulation Environment (ASE) calculator, which is then used to perform structure relaxation and phonon calculations with the default settings of the benchmark. For comparison, we consider only models in the compliant subset of the benchmark. This consists only of models that are trained on MPtrj or subsets, which limits data leakage and offers a more fair comparison among methods. Table 1 contains the performance of Nequix along with all current compliant models at the time of writing. We also include the reported training cost for the models when available, visualized in Fig. 1. We find that Nequix ranks third by CPS, outperforming most models at a fraction of the training cost. It is noteworthy that this high ranking is due to high performance in the thermal conductivity task, however the F1 score is still comparable to many of the other methods.

Table 1: Matbench-Discovery compliant leaderboard, sorted by combined performance score (CPS). Metrics are shown for the unique prototypes subset. Train cost is measured in A100 hours.

Model	Params	Train cost	RMSD↓	κ_{SRME} ↓	F1↑	CPS↑
eSEN-30M-MP	30.1M		0.075	0.340	0.831	0.797
Eqnorm MPtrj	1.31M	2000	0.084	0.408	0.786	0.756
Nequix	707K	500	0.085	0.446	0.750	0.729
DPA-3.1-MPtrj	4.81M		0.080	0.650	0.803	0.718
SevenNet-l3i5	1.17M		0.085	0.550	0.760	0.714
HIENet	7.51M	2888	0.080	0.642	0.777	0.707
MatRIS v0.5.0 MPtrj	5.83M		0.077	0.861	0.809	0.681
GRACE-2L-MPtrj	15.3M		0.090	0.525	0.691	0.681
MACE-MP-0	4.69M	2600	0.092	0.647	0.669	0.644
eqV2 S DeNS	31.2M		0.076	1.676	0.815	0.522
ORB v2 MPtrj	25.2M		0.101	1.725	0.765	0.470
M3GNet	228k		0.112	1.412	0.569	0.428
CHGNet	413k		0.095	1.717	0.613	0.400

3.2 MDR phonon benchmark

We also evaluate performance on the MDR phonon benchmark [Loew et al., 2025], a set of 10,000 phonon calculations also done with DFT/PBE level of theory. We follow the identical procedure to Loew et al. [2025], first performing a geometry relaxation, then phonon calculations using displacements of supercell. Mean absolute error (MAE) of properties derived from the phonon calculation: maximum phonon frequency ω_{\max} , vibrational energy S , Helmholtz free energy F , and heat capacity at constant volume C_V . Table 2, demonstrates the performance of Nequix compared to other MPtrj-trained models. Similarly to Matbench-Discovery, we achieve performance within the top three of models, with a fraction of the parameter count of other methods.

Table 2: Model performance of MPtrj-trained models on the MDR phonon benchmark, sourced from Loew et al. [2025] and Fu et al. [2025].

Model	MAE(ω_{\max})	MAE(S)	MAE(F)	MAE(C_V)
eSEN-30M	21	13	5	4
SevenNet-13i5	26	28	10	5
Nequix	26	33	12	6
SevenNet-0	40	48	19	9
GRACE-2L (r6)	40	25	9	5
MACE	61	60	24	13
CHGNet	89	114	45	21
M3GNet	98	150	56	22

3.3 Inference speed

Lastly, we compare inference speed against existing materials potentials using a script from the MACE [Batatia et al., 2022] repository¹, modified to work with Nequix and eSEN. We run each model in the configuration in which it is used within its ASE calculator, without compilation for the PyTorch-based MACE-MP-0 and eSEN models, and just-in-time compilation for the JAX-based Nequix. Figure 3 compares performance of each model in terms of steps per day vs. number of atoms. In this study, Nequix is about $10\times$ faster than eSEN, and roughly $2\times$ slower than MACE-MP-0, offering a new option in the accuracy vs. speed Pareto frontier at a fraction of the training cost.




Figure 3: Inference speed of various models in steps per day.

4 Conclusion

We presented Nequix, an E(3)-equivariant interatomic potential that pairs a simplified NequIP architecture with modern training practices. Our results show that Nequix achieves competitive accuracy on Matbench-Discovery and the MDR phonon benchmark at less than one quarter of the reported training cost of many contemporaries. This resource-efficient recipe provides a practical alternative to large-scale foundation models and helps broaden access to high-quality atomistic modeling in settings with more limited compute. We release trained weights and a JAX codebase to streamline reuse and extension.

Looking ahead, we see several promising directions: scaling training duration and data while maintaining budget discipline, exploring pretraining and fine-tuning regimes across broader datasets, and pushing cost even lower through model distillation, pruning, quantization, kernel-implementations, or more data-efficient training. We hope Nequix serves as a strong, efficient baseline for future work on accessible materials foundation models.

¹https://github.com/ACESuit/mace/blob/main/tests/test_benchmark.py

Acknowledgments and Disclosure of Funding

We thank Mit Kotak for helpful discussions and insights. This work was supported by the National Science Foundation under Cooperative Agreement PHY-2019786 (The NSF AI Institute for Artificial Intelligence and Fundamental Interactions, <http://iaifi.org/>) and by DOE ICDI grant DE-SC0022215. This research used resources of the National Energy Research Scientific Computing Center (NERSC), a Department of Energy User Facility using NERSC award ERCAP0033254.

References

- Ilyes Batatia, Philipp Benner, Yuan Chiang, Alin M Elena, Dávid P Kovács, Janosh Riebesell, Xavier R Advincula, Mark Asta, Matthew Avaylon, William J Baldwin, et al. A foundation model for atomistic materials chemistry. *arXiv preprint arXiv:2401.00096*, 2023.
- Janosh Riebesell, Rhys EA Goodall, Philipp Benner, Yuan Chiang, Bowen Deng, Gerbrand Ceder, Mark Asta, Alpha A Lee, Anubhav Jain, and Kristin A Persson. A framework to evaluate machine learning crystal stability predictions. *Nature Machine Intelligence*, 7(6):836–847, 2025.
- Simon Batzner, Albert Musaelian, Lixin Sun, Mario Geiger, Jonathan P Mailoa, Mordechai Kornbluth, Nicola Molinari, Tess E Smidt, and Boris Kozinsky. E (3)-equivariant graph neural networks for data-efficient and accurate interatomic potentials. *Nature communications*, 13(1):2453, 2022.
- Keller Jordan, Jeremy Bernstein, Brendan Rappazzo, @fernbear.bsky.social, Boza Vlado, You Jiacheng, Franz Cesista, Braden Koszarsky, and @Grad62304977. modded-nanogpt: Speedrunning the nanogpt baseline, 2024a. URL <https://github.com/KellerJordan/modded-nanogpt>.
- Keller Jordan, Yuchen Jin, Vlado Boza, Jiacheng You, Franz Cesista, Laker Newhouse, and Jeremy Bernstein. Muon: An optimizer for hidden layers in neural networks, 2024b. URL <https://kellerjordan.github.io/posts/muon/>.
- Antoine Loew, Dewen Sun, Hai-Chen Wang, Silvana Botti, and Miguel AL Marques. Universal machine learning interatomic potentials are ready for phonons. *npj Computational Materials*, 11(1):178, 2025.
- Chi Chen and Shyue Ping Ong. A universal graph deep learning interatomic potential for the periodic table. *Nature Computational Science*, 2(11):718–728, 2022.
- Bowen Deng, Peichen Zhong, KyuJung Jun, Janosh Riebesell, Kevin Han, Christopher J Bartel, and Gerbrand Ceder. Chgnet as a pretrained universal neural network potential for charge-informed atomistic modelling. *Nature Machine Intelligence*, 5(9):1031–1041, 2023.
- Anton Bochkarev, Yury Lysogorskiy, and Ralf Drautz. Graph atomic cluster expansion for semilocal interactions beyond equivariant message passing. *Physical Review X*, 14(2):021036, 2024.
- Mark Neumann, James Gin, Benjamin Rhodes, Steven Bennett, Zhiyi Li, Hitarth Choubisa, Arthur Hussey, and Jonathan Godwin. Orb: A fast, scalable neural network potential. *arXiv preprint arXiv:2410.22570*, 2024.
- Luis Barroso-Luque, Muhammed Shuaibi, Xiang Fu, Brandon M Wood, Misko Dzamba, Meng Gao, Ammar Rizvi, C Lawrence Zitnick, and Zachary W Ulissi. Open materials 2024 (omat24) inorganic materials dataset and models. *arXiv preprint arXiv:2410.12771*, 2024.
- Xiang Fu, Brandon M Wood, Luis Barroso-Luque, Daniel S Levine, Meng Gao, Misko Dzamba, and C Lawrence Zitnick. Learning smooth and expressive interatomic potentials for physical property prediction. *arXiv preprint arXiv:2502.12147*, 2025.
- Duo Zhang, Anyang Peng, Chun Cai, Wentao Li, Yuanchang Zhou, Jinzhe Zeng, Mingyu Guo, Chengqian Zhang, Bowen Li, Hong Jiang, et al. Graph neural network model for the era of large atomistic models. *arXiv preprint arXiv:2506.01686*, 2025.
- Keqiang Yan, Montgomery Bohde, Andrii Kryvenko, Ziyu Xiang, Kaiji Zhao, Siya Zhu, Saagar Kolachina, Doğuhan Sarıtürk, Jianwen Xie, Raymundo Arróyave, et al. A materials foundation model via hybrid invariant-equivariant architectures. *arXiv preprint arXiv:2503.05771*, 2025.
- Yutack Park, Jaesun Kim, Seungwoo Hwang, and Seungwu Han. Scalable parallel algorithm for graph neural network interatomic potentials in molecular dynamics simulations. *Journal of chemical theory and computation*, 20(11):4857–4868, 2024.
- Yi-Lun Liao, Brandon Wood, Abhishek Das, and Tess Smidt. Equiformerv2: Improved equivariant transformer for scaling to higher-degree representations. *arXiv preprint arXiv:2306.12059*, 2023.

- James Bradbury, Roy Frostig, Peter Hawkins, Matthew James Johnson, Chris Leary, Dougal Maclaurin, George Necoala, Adam Paszke, Jake VanderPlas, Skye Wanderman-Milne, and Qiao Zhang. JAX: composable transformations of Python+NumPy programs, 2018. URL <http://github.com/jax-ml/jax>.
- Patrick Kidger and Cristian Garcia. Equinox: neural networks in JAX via callable PyTrees and filtered transformations. *Differentiable Programming workshop at Neural Information Processing Systems 2021*, 2021.
- Daniel T Speckhard, Tim Bechtel, Sebastian Kehl, Jonathan Godwin, and Claudia Draxl. Analysis of static and dynamic batching algorithms for graph neural networks. *arXiv preprint arXiv:2502.00944*, 2025.
- Jonathan Godwin*, Thomas Keck*, Peter Battaglia, Victor Bapst, Thomas Kipf, Yujia Li, Kimberly Stachenfeld, Petar Veličković, and Alvaro Sanchez-Gonzalez. Jraph: A library for graph neural networks in jax., 2020. URL <http://github.com/deepmind/jraph>.
- Diederik P Kingma and Jimmy Ba. Adam: A method for stochastic optimization. *arXiv preprint arXiv:1412.6980*, 2014.
- Anubhav Jain, Shyue Ping Ong, Geoffroy Hautier, Wei Chen, William Davidson Richards, Stephen Dacek, Shreyas Cholia, Dan Gunter, David Skinner, Gerbrand Ceder, et al. Commentary: The materials project: A materials genome approach to accelerating materials innovation. *APL materials*, 1(1), 2013.
- Ilyes Batatia, David Peter Kovacs, Gregor N. C. Simm, Christoph Ortner, and Gabor Csanyi. MACE: Higher order equivariant message passing neural networks for fast and accurate force fields. In Alice H. Oh, Alekh Agarwal, Danielle Belgrave, and Kyunghyun Cho, editors, *Advances in Neural Information Processing Systems*, 2022. URL <https://openreview.net/forum?id=YPpSngE-ZU>.

A Appendix

A.1 Training and model configuration

Table A1 shows the hyper-parameters used to train Nequix. The model is trained for 100 epochs, using an MAE loss function on energy and stress, and l_2 loss on forces. We use a linear warmup with cosine decay learning rate schedule.

Table A1: Hyper-parameters used and rationale behind selection

Hyper-parameter	Value	Notes/Rational
Radial cutoff	6 Å	Most models, use 5 or 6 Å; 6 performed slightly better in preliminary validation performance.
Hidden irreps	128x0e + 64x1o + 32x2e + 32x3o	From SevenNet-13i5.
L_{\max}	3	Consistent with hidden irreps.
N_{layers}	4	Balance of performance and efficiency.
Radial basis size	8	From NequIP and analysis from Sec. 5.2 of Fu et al. [2025]
Radial MLP size	64	From NequIP.
Radial MLP layers	2	From NequIP.
Polynomial cutoff p	6.0	From NequIP.
Radial basis function	Bessel	From NequIP. Also tried Gaussian, which had minimal difference on validation performance.
Learning rate	0.01	Selected from {0.03, 0.01, 0.003, 0.001} based on validation performance early in training.
Warmup epochs	0.1	From eSEN.
Warmup factor	0.2	From eSEN.
Optimizer	Muon	See Sec. 2.
Weight decay	0.001	From eSEN. Also tried 0.0, which lead to worse validation performance.
Energy weight	20	From eSEN.
Force weight	20	From eSEN.
Stress weight	5	From eSEN.
Batch size	256 (dynamic)	See Sec. 2
Number of epochs	100	Standard training duration.